

无锡市聚邦助剂有限公司

WUXI JUBANG AUXILIARIES CO., LTD

Test Report

		i	1
Name	PVC Resin SG-5	Inspected unit	Headquarter
Batch No.	HSHZJ8-CP12.5	Sample selected	Laboratory
Quantity	2656 t	Inspection Date	2015.12.23
Test basis	GB/T 5761-2006		
Test Items	Index	Test result	Assessment
Viscosity	118~107	110	Pass
K Value	66~68		Pass
Polymerization Degree	1000~1100		Pass
Impurity Particle	≤16pcs/100g	12	Pass
Volatile Content	≤0.40%	0.10	Pass
Apparent density	≥0.48g/ml	0.54	Pass
Sieve Residue (250µm)	≤2.0%	0.1	Pass
Sieve Residue (63μm)	≥95%	99.6	Pass
Fish eyes	≤20pc/400cm ²	12	Pass
Plasticizer Absorbency Value of 100g Resin	≥19g	23	Pass
Whiteness(160°C,10min)	≥78%	84	Pass
Residue Chlorethylene Content	≤5μg/g	0.2	Pass

Conclusion: This batch is high quality.